

BAL15Y

Code(d) **557587**

Code(e) **559585**

Refractive Index n_d	1.55671 1.556711	Abbe Number v_d	58.7 58.68	Dispersion n_F-n_C	0.00948 0.009488
Refractive Index n_e	1.558973	Abbe Number v_e	58.41	Dispersion $n_F-n_{C'}$	0.009569

Refractive Indices		
$\lambda(\mu m)$		
n_{2325}	2.32542	1.52907
n_{1970}	1.97009	1.53423
n_{1530}	1.52958	1.53972
n_{1129}	1.12864	1.54449
n_t	1.01398	1.54604
n_s	0.85211	1.54872
$n_{A'}$	0.76819	1.55053
n_r	0.70652	1.55218
n_C	0.65627	1.55383
$n_{C'}$	0.64385	1.55429
n_{He-Ne}	0.6328	1.55471
n_D	0.58929	1.55663
n_d	0.58756	1.55671
n_e	0.54607	1.55897
n_F	0.48613	1.56331
$n_{F'}$	0.47999	1.56385
n_{He-Cd}	0.44157	1.56779
n_g	0.435835	1.56848
n_h	0.404656	1.57277
n_i	0.365015	1.58012
n_{334}	0.334148	1.58807
n_{326}	0.326106	1.59060

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta \theta_{C,t}$	-0.0015
$\Delta \theta_{C,A'}$	0.0004
$\Delta \theta_{g,d}$	-0.0026
$\Delta \theta_{g,F}$	-0.0021
$\Delta \theta_{i,g}$	-0.0073

Constants of Dispersion Formula *1	
A_1	1.28348331E+00
A_2	1.02800765E-01
A_3	4.04609885E-01
B_1	7.90900515E-03
B_2	3.05971274E-02
B_3	4.65268356E+01

Other Properties	
Bubble Quality Group B	
Specific Gravity d	2.9
Remarks	

Temperature Coefficients of Refractive Index								
Range of Temperature (°C)	dn/dt relative (10 ⁻⁶ /°C)							
	t	C'	He-Ne	D	e	F'	g	i
-40~20	2.2	2.5	2.5	2.6	2.8	3.0	3.3	4.2
-20~0	2.2	2.5	2.6	2.7	2.8	3.1	3.5	4.3
0~20	2.3	2.6	2.6	2.8	2.9	3.2	3.6	4.5
20~40	2.4	2.7	2.7	2.8	3.0	3.3	3.7	4.6
40~60	2.4	2.8	2.8	2.9	3.1	3.4	3.8	4.8
60~80	2.4	2.8	2.9	3.0	3.1	3.5	3.9	4.9

Partial Dispersions	
n_C-n_t	0.007785
$n_C-n_{A'}$	0.003296
n_d-n_C	0.002885
n_e-n_C	0.005147
n_g-n_d	0.011768
n_g-n_F	0.005165
n_h-n_g	0.004295
n_i-n_g	0.011636
n_C-n_t	0.008244
$n_e-n_{C'}$	0.004688
$n_{F'}-n_e$	0.004881
$n_{F'}-n_{F'}$	0.016261

Thermal Properties	
Strain Point StP (°C)	
Annealing Point AP (°C)	
Transformation Temperature Tg (°C)	507
Yield Point At (°C)	547
Softening Point SP (°C)	642
Expansion Coefficients (-30~+70°C)	76
α (10 ⁻⁷ /°C) (+100~+300°C)	90
Thermal Conductivity k (W/m-K)	1.000

Mechanical Properties	
Young's Modulus E (10 ⁸ N/m ²)	783
Rigidity Modulus G (10 ⁸ N/m ²)	317
Poisson's Ratio σ	0.236
Knoop Hardness Hk[Class]	560 6
Abrasion Aa	113
Photoelastic Constant β (nm/cm/10 ⁶ Pa)	

*1 By using these contents, refractive indices for any wavelength between 326 and 1129nm can be calculated. When calculateing refractive indices for any wavelength between 1129 and 2325nm, please refer to us.

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	1
Acid Resistance(Surface) Group SR	1.2
Phosphate Resistance PR	1.0

Relative Partial Dispersions	
$\theta_{C,t}$	0.8205
$\theta_{C,A'}$	0.3474
$\theta_{d,C}$	0.3041
$\theta_{e,C}$	0.5425
$\theta_{g,d}$	1.2403
$\theta_{g,F}$	0.5444
$\theta_{h,g}$	0.4527
$\theta_{i,g}$	1.2264
$\theta'_{C,t}$	0.8615
$\theta'_{e,C'}$	0.4899
$\theta'_{F',e}$	0.5101
$\theta'_{i,F}$	1.6993

Coloring			
λ_{80}	32	λ_5	30

Internal Transmittance		
λ (nm)	τ_{10mm}	τ_{25mm}
240		
250		
260		
270		
280		
290		
300	0.17	0.01
310	0.59	0.27
320	0.84	0.65
330	0.937	0.85
340	0.971	0.929
350	0.985	0.963
360	0.992	0.979
365	0.994	0.984
370	0.995	0.988
380	0.996	0.990
390	0.997	0.993
400	0.998	0.994
420	0.998	0.995
440	0.998	0.995
460	0.998	0.996
480	0.998	0.996
500	0.999	0.997
550	0.999	0.997
600	0.999	0.997
650	0.998	0.996
700	0.999	0.997
800	0.999	0.997
900	0.998	0.995
1000	0.996	0.990
1200	0.995	0.988
1400	0.989	0.972
1600	0.992	0.980
1800	0.984	0.961
2000	0.972	0.932
2200	0.927	0.82
2400	0.89	0.75