

S-NBH 5

Code(d) **654397**

Code(e) **658395**

Refractive Index n_d	1.65412	Abbe Number v_d	39.7	Dispersion n_F-n_C	0.01648
	1.654115		39.68		0.016484
Refractive Index n_e	1.658026	Abbe Number v_e	39.43	Dispersion n_F-n_C'	0.016687

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.61410
n_{1970}	1.97009	1.62070
n_{1530}	1.52958	1.62787
n_{1129}	1.12864	1.63448
n_t	1.01398	1.63677
n_s	0.85211	1.64090
$n_{A'}$	0.76819	1.64379
n_r	0.70652	1.64649
n_C	0.65627	1.64923
$n_{C'}$	0.64385	1.65000
$n_{\text{He-Ne}}$	0.6328	1.65072
n_D	0.58929	1.65397
n_d	0.58756	1.65412
n_e	0.54607	1.65803
n_F	0.48613	1.66571
$n_{F'}$	0.47999	1.66668
$n_{\text{He-Cd}}$	0.44157	1.67389
n_g	0.435835	1.67517
n_h	0.404656	1.68331
n_i	0.365015	1.69791

Partial Dispersions	
n_C-n_t	0.012452
$n_C-n_{A'}$	0.005432
n_d-n_C	0.004890
n_e-n_C	0.008801
n_g-n_d	0.021051
n_g-n_F	0.009457
n_h-n_g	0.008144
n_i-n_g	0.022741
n_C-n_t	0.013223
$n_e-n_{C'}$	0.008030
$n_{F'-n_e}$	0.008657
$n_i-n_{F'}$	0.031224

Relative Partial Dispersions	
$\theta_{C,t}$	0.7554
$\theta_{C,A'}$	0.3295
$\theta_{d,C}$	0.2967
$\theta_{e,C}$	0.5339
$\theta_{g,d}$	1.2771
$\theta_{g,F}$	0.5737
$\theta_{h,g}$	0.4941
$\theta_{i,g}$	1.3796
$\theta'_{C,t}$	0.7924
$\theta'_{e,C'}$	0.4812
$\theta'_{F',e}$	0.5188
$\theta'_{i,F}$	1.8712

Thermal Properties	
Strain Point StP (°C)	489
Annealing Point AP (°C)	511
Transformation Temperature Tg (°C)	524
Yield Point At (°C)	575
Softening Point SP (°C)	645
Expansion Coefficients (-30~+70°C)	66
α (10 ⁻⁷ /°C) (+100~+300°C)	84
Thermal Conductivity k (W/m·K)	0.965

Coloring			
λ_{80}	37	λ_5	33
λ_{70}			

Internal Transmittance	
$\lambda(\text{nm})$	$\tau_{10\text{mm}}$
280	
290	
300	
310	
320	
330	0.12
340	0.47
350	0.71
360	0.83
370	0.902
380	0.936
390	0.957
400	0.969
420	0.980
440	0.985
460	0.988
480	0.991
500	0.994
550	0.997
600	0.997
650	0.997
700	0.998
800	0.999
900	0.999
1000	0.999
1200	0.999
1400	0.991
1600	0.994
1800	0.989
2000	0.976
2200	0.919
2400	0.80

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0226
$\Delta\theta_{C,A'}$	0.0056
$\Delta\theta_{g,d}$	-0.0052
$\Delta\theta_{g,F}$	-0.0036
$\Delta\theta_{i,g}$	-0.0132

Mechanical Properties	
Young's Modulus E (10 ⁸ N/m ²)	902
Rigidity Modulus G (10 ⁸ N/m ²)	361
Poisson's Ratio σ	0.248
Knoop Hardness Hk[Class]	580 6
Abrasion Aa	130
Photoelastic Constant β (nm/cm/10 ⁵ Pa)	3.22

Constants of Dispersion Formula	
A ₁	1.47544521E+00
A ₂	1.93060095E-01
A ₃	1.50939010E+00
B ₁	9.55836740E-03
B ₂	4.60430483E-02
B ₃	1.26422746E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	2
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	1.0

Other Properties	
Bubble Quality Group B	
Specific Gravity d	3.02
Remarks	

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	dn/dt relative (10 ⁻⁶ /°C)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	3.5	4.1	4.1	4.3	4.6	5.1	5.8
-20~ 0	3.6	4.2	4.2	4.5	4.7	5.3	6.0
0~20	3.7	4.3	4.4	4.6	4.9	5.5	6.2
20~40	3.8	4.4	4.5	4.8	5.0	5.7	6.4
40~60	3.9	4.6	4.6	4.9	5.1	5.8	6.6
60~80	3.9	4.7	4.7	5.0	5.3	6.0	6.8